

OTB Architectural Elements, Inc.
Tel: 877-927-7192
Fax: 954-927-7349
Web site: www.otbae.com
E-mail: sales@otbae.com

Testing

ResinKast™ PRODUCT TESTING AND EVALUATION

Unlike any other texturized product in the building industry, OTB's ResinKast™ products have been successfully subjected to a number of tests to qualify for Florida State Product Approval.

The following is a summary of the official test results conducted by State approved Laboratories in accordance to Florida Building Codes. Actual test results are available upon demand:

Test Description	Measured	Remarks
Uniform Wind Load (ASTM E-330)		
Structural Load Test		
Positive Load	112.5 PSF	Passed
Negative Load	112.5 PSF	Passed
 Uniform Design Load Test		
 Positive Load	 150.0 PSF	 Passed
Negative Load	150.0 PSF	Passed
 Uniform Structural Load Test		
Positive Load	225.0 PSF	Passed
Negative Load	225.0 PSF	Passed
 Surface Burning Characteristics (ASTM E-84)		
Flame Spread Index	20	Satisfactory
Smoke Developed Index	225	Satisfactory
 Self-Ignition Temperature (ASTM D-1929-96)		
Minimum Above 650 Degrees F	940 Degrees F	Meets Requirement
 Outdoor Durability Test (ASTM G-155)		
	4500 Hours	Successful