



## Concrete Coatings Clear Siliconized Acrylic Sealer 3708-XXXX

Previously ICI Paints GROUNDWORKS™  
Solvent-Based Clear Siliconized Acrylic Concrete Sealer

### DESCRIPTION

A solvent-based clear siliconized acrylic sealer formulated for use on horizontal unpainted concrete and masonry surfaces such as driveways, garage floors, patios, walkways, decks, pool decks and sidewalks. Provides a durable, hard clear semi-gloss finish that is highly impact and abrasion resistant. Not recommended for previously painted, asphalt or wood surfaces.

### CERTIFICATIONS

AS OF 7/1/2009, COMPLIES WITH	
MPI#	104
LEED	No
CHPS	No
GREENGUARD	No
AIM	No
OTC/LADCO	No
CARB	No
SCAQMD	No

### PERFORMANCE DATA

CHARACTERISTIC:	RESULTS:
Adhesion*	★★★★★★★☆☆☆
Moisture Resistance*	★★★★★★★☆☆☆
Abrasion Resistance*	★★★★★★★☆☆☆
Air and Substrate Application Temperature	50° F (10° C) - 75° F (24° C)
Service Temperature Limits	200° F (93° C)
Storage Temperature	40° F (4° C) - 75° F (24° C)

\*Performance ratings are based on product comparisons to other products in that sheen range, performed at 77° F (25° C) 50% RH. Rating scale is from 1-10, 10 being the highest rating.

### COMPOSITION

- Silicone Acrylic Resin
- Not manufactured with lead or mercury containing materials.

### SPECIFICATION

Color:  
Clear

Clean-up Solvent:  
Xylene

Finish: **Semi-Gloss**  
Gloss: 75 units maximum @ 60°

Density:  
7.74 lbs/gal (1.93 kg/L)

Solids:  
Volume - 26% +/- 2%  
Weight - 30% +/- 2%

VOC:  
598 g/L (4.99 lbs/gal)  
Refer to MSDS for regulatory VOC content of complete product line

Theoretical Coverage @ 1 mil dry:  
415 sq ft/gal (10 m<sup>2</sup>/L)

Practical Coverage:  
Apply at 300-500 sq ft/gal (7-12 m<sup>2</sup>/L).  
Actual coverage may vary depending on substrate and application method.

Recommended Film Thickness:  
3.2 - 5.3 mils wet  
0.8 - 1.4 mils dry

Airless Spray Application:  
Pressure - 2000 psi  
Tip - .015" - .017"

Dry Time 77°F (25°C) & 50% RH:  
To touch - 6 hours  
To recoat - 12 hours  
To light foot traffic - 12 hours  
To vehicular traffic - 72 hours

Flame Spread Rating:  
Class A (0-25) on non-combustible surfaces

Flash Point:  
80° F (27° C)

Shelf Life:  
1 year minimum - unopened



www.gliddenprofessional.com

9 FINISHES  
PAINTING (09900)

**DANGER! FLAMMABLE. HARMFUL OR FATAL IF SWALLOWED. VAPOR HARMFUL.**

Read Label and Material Safety Data Sheet Prior to Use. See other cautions on last page. DSF11-0400



## SURFACE PREPARATION

### GENERAL SURFACE PREPARATION:

All surfaces must be sound, dry, clean and free of oil, grease, rust, dirt, mildew, paint and other foreign substances.

### NEW MASONRY SURFACES:

- Cure at least 30 days before painting. pH must be 10.0 or lower
- Roughen slick poured or precast concrete and remove sealers by chemical cleaning or abrasive method such as sandsweeping
- Rinse thoroughly with water and allow to dry
- Remove loose aggregate
- Seal with this product

### PREVIOUSLY PAINTED MASONRY SURFACES:

- Not recommended over previously painted surfaces

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear an NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

## SHIPPING

### FREIGHT CLASSIFICATION:

Paint, 3, UN1263, PGIII

### PACKAGING:

1 gallon (3.785 L)  
5 gallons (18.925 L)

### FLASH POINT:

80° F (27° C)

## DIRECTIONS FOR USE

### TINTING:

Do not tint.

### SPREADING RATE:

Apply at 300-500 sq ft/gal (7-12 m<sup>2</sup>/L). Varies depending on type of surface and porosity. **SPREAD SHEET 375-425 sq ft/gal (m<sup>2</sup>/L) ANVIL update no changes**

### APPLICATION:

Mix thoroughly and stir frequently while using. Apply by brush (do not use a nylon brush, use a natural bristle brush), roller or airless spray. For airless spray application, use a .015"-.017" tip at 2000 psi, adjust pressure as needed. Always keep a wet edge to avoid lap marks. AVOID HEAVY APPLICATIONS OR PUDDLING ON HORIZONTAL SURFACES. REMOVE EXCESS BEFORE DRYING. Apply product in thin multiple coats for best results. Do not apply when surface or air temperature is below 50° F (10° C). Do not paint, if rain, snow or heavy dew is expected within 48 hours. Do not apply to an excessively hot surface, which may result in rapid drying and poor surface penetration.

**CAUTION:** Surfaces coated with this product may become slippery when wet. For additional slip resistance in areas of pedestrian traffic, add 3001 Concrete Coatings Slip Resistant Additive at 0.18 lbs (2.9 oz) per gallon or 0.88 lbs (14 oz) per five gallons of product.

### DRYING TIME:

At 77° F (25° C) and 50% R.H., dries to touch in six hours and to recoat in 12 hours. Dries to light foot traffic in 12 hours and to vehicular traffic in 72 hours. Low temperature or high humidity will increase these times.

### CLEAN-UP:

Clean tools immediately with xylene. Clean spills right away with a damp cloth.

## PRECAUTIONS

**DANGER! FLAMMABLE LIQUID AND VAPOR. HARMFUL OR FATAL IF SWALLOWED. ASPIRATION HAZARD - CAN ENTER LUNGS AND CAUSE DAMAGE. HARMFUL IF INHALED. MAY CAUSE CENTRAL NERVOUS SYSTEM EFFECTS, INCLUDING DIZZINESS, HEADACHE OR NAUSEA. CAUSES EYE, SKIN AND RESPIRATORY TRACT IRRITATION. OVEREXPOSURE MAY CAUSE BLOOD, LIVER, KIDNEY DAMAGE. USE ONLY WITH ADEQUATE VENTILATION. KEEP OUT OF THE REACH OF CHILDREN. NOTICE:** Products in this series contain solvents. Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal. For emergency information call (800) 545-2643. **Note:** These warnings encompass the product series. **Prior to use, read and follow product-specific MSDS and label information.** Keep away from heat, sparks and flame. **Do not smoke.** Vapors may ignite. Extinguish all flames, burners, stoves, heaters and pilot lights and disconnect all electrical motors and appliances before use and until all vapors are gone. Prevent build-up of vapors by opening all windows and doors to achieve cross-ventilation. If sanding, wear a dust mask to avoid breathing of sanding dust. Do not breathe vapors or spray mist. Ensure fresh air entry during application and drying. Avoid contact with eyes and skin. If you experience eye watering, headaches, or dizziness, leave the area. If properly used, a respirator may offer additional protection. Obtain professional advice before using. Close container after each use. **FIRST AID:** For skin contact, wash thoroughly with soap and water. If any product remains, gently rub with petroleum jelly, vegetable or mineral/baby oil then wash again with soap and water. Repeat as needed. Remove contaminated clothing. For eye contact, flush immediately with plenty of water for at least 15 minutes. **Get medical attention.** If swallowed, **get medical attention immediately.** If inhalation causes discomfort, remove to fresh air. If discomfort persists or breathing difficulty occurs, get medical attention. **KEEP FROM FREEZING.** DS154-0806



Akzo Nobel Paints LLC, Strongsville, Ohio 44136



www.gliddenprofessional.com

**LIMITATION OF LIABILITY** To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance but are subject to change without prior notice. We guarantee our product to conform to the specifications contained herein. **WE MAKE NO OTHER WARRANTY OR GUARANTEE OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE.** Liability, if any, is limited to replacement of the product or refund of the purchase price. **LABOR OR COST OF LABOR AND OTHER CONSEQUENTIAL DAMAGES ARE HEREBY EXCLUDED.**