

WallBar

Technical Data

CAN/ULC-S703 and NRC/CCMC Test Data

Thermal Resistance Attic	RSI-0.0266/mm (R-3.84/inch)
Thermal Resistance Wall	RSI-0.0263/mm (R-3.79/inch)
Flame Spread Classification:	
- As per CAN/ULC-S 102	FSC 20
- As per CAN/ULC-S 102.2	FSC 120
Flame Spread Permanence	Passed
Moisture Absorption	<10% w/w
Fungi Resistance	Passed
Corrosion Resistance	Passed/td>
Smolder Resistance	Passed
Coverage Density Attic	24.8 kg/m ³ (1.55 lb/ft ³)
Coverage Density Wall	44.5 kg/m ³ (2.78 lb/ft ³)